



Thermoplastic Polyurethane
热塑性聚氨酯

Technical DataSheet
技术数据表

ProductName 产品名称	S-198AL
----------------------------	----------------

Polyester TPU-S100 Series/ 聚酯型TPU – S100系列

Injection molding, short cycle times, good mechanical properties
适用于注塑成型, 成型快, 良好的机械性能
Generic grade
广泛通用级

Applications
应用

Typical application : electric wire and cable , cart wheels , phone sets etc
典型用途: 电线电缆、推车轮、手机套等产品

Physical Properties 物理特性	Test Standard 测试标准	Unit 单位	Typical Value* 平均值
Density 密度	ASTM D792	g/cm ³	1.23±0.02
Shore Hardness 肖氏硬度	ASTM D2240	Shore A Shore D	98A±2 A
Tensile Strength 拉伸强度	ASTM D412	Kgf/cm ²	350
Elongation at Break 最大伸长	ASTM D412	%	400
100% Tensile Strength 拉伸强度@100%伸长	ASTM D412	Kgf/cm ²	120
300% Tensile Strength 拉伸强度@300%伸长	ASTM D412	Kgf/cm ²	150
Tear Strength 撕裂强度	ASTM D624	Kgf/cm	130

Molding Conditions 成型条件

Drying 干燥	Drying Temperature 干燥温度	100°C
	Drying Time 干燥时间	2-4hrs
Processing 成型	Processing Temperature 建议成型温度	190-215 °C
	Processing Mold 建议成型方式	Injection Molding 注塑成型

* Typical values, should not equal to the true values, different processing and test conditions will result in the difference values, please confirm all results by own tests.
平均值, 不能等同于真实值, 不同的加工过程和测试条件将会导致不同的结果, 请亲自测试以进行确认.

Note: Additional information (Storage, Drying, processing, Coloring, Post Treatment, Recycling, etc.), please contact our sales representative or technical service representative.
存贮, 干燥, 加工, 着色, 后处理, 再生等更详细的信息请联系我们的销售代表和技术服务代表.